

# Item Description

## Item ID

PRE-ELEC<sup>®</sup> CC7602  
CC7602

PE extrusion compound

Typical end product  
Cable

Applications  
Semiconductive cable jacket

PRE-ELEC<sup>®</sup> CC7602 is a semiconductive thermoplastic compound based on polyethylene for cable jacketing applications for USA and North America region. It is engineered to have excellent ESCR-properties with premium surface quality and dispersion of carbon black. It is easy to extrude with high and consistent level of quality.

Designed to meet the standards: IEC 60502-2, IEC 60840, IEC 62067, IEC 62895 ST7, ICEA S-94-649, ICEA S-97-682 and ICEA S-108-720 Type II.

Special properties	Unit	Value	Method
Volume resistivity(* 23 °C	Ω.cm	50	PRE021
General properties	Unit	Value	Method
Density	g/cm <sup>3</sup>	1,07	ISO 1183
Melt flow rate at 190°C	g/10 min		ISO 1133
5.0 kg		1,5	
21.6 kg		18	
Mechanical properties	Unit	Value	Method
Stress at break(*	MPa	29	ISO 527
Strain at break(*	%	>500	ISO 527
Change of tensile properties after ageing	%		
110°C, 240h		<20	
121°C, 168h		<25	
Hardness, Shore D	-	60	ISO 868

MFR is measured from granulates. Tensile test speed: 25 mm/min, Sample test length 50mm

Test specimen: injection moulded rod; ISO 527 TYPE 1A; Thickness: 10 mm, width: 4 mm

(\* extruded tape; ISO 527-2 Type 5A, thickness 1 500 - 2 000 µm



Item Description  
Item ID

PRE-ELEC<sup>®</sup> CC7602  
CC7602

Visit Premix Data Center for more detailed information of our products at [www.premixgroup.com/data-center/](http://www.premixgroup.com/data-center/)

Processing instructions

	Unit	Processing range
Extrusion		
Cylinder temperature profile	°C	180 - 240
Die temperature profile	°C	210 - 250

Notes

Drying of the product is recommended for 2-3 hours at 60-80°C prior to use.

These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns. Overheated material can be cooled with e.g. water.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC<sup>®</sup> is a registered trademark of Premix.