

Item Description

Item ID

PRE-ELEC[®] CC2201
CC2201

Cable extrusion compound
Semiconductive
PP-TPE

Typical end product
High and Medium Voltage Cables

Applications
Conductor Screen
Insulation Screen

PRE-ELEC[®] CC 2201 is a thermoplastic cable compound designed for conductor screen and insulation screen layers for high voltage and medium voltage PP-TPE power cable applications. It has well balanced material and electrical properties with premium surface quality and dispersion of carbon black. It is easy to extrude with high and consistent level of quality.

This product is compliant with HD 620 S3 Part 12 standard requirements.

Special properties	Unit	Value	Method
Volume resistivity(*)	Ω.cm		PRE021
23°C		30	
90°C		<100	
General properties	Unit	Value	Method
Density	g/cm ³	0,99	ISO 1183
Melt flow rate at 230°C	g/10 min		ISO 1133
5.0 kg		3	
Mechanical properties	Unit	Value	Method
Stress at break(*)	MPa	30	ISO 527
Strain at break(*)	%	>450	ISO 527
Change of tensile properties after ageing 135°C, 240 h	%	<20	
Flexural modulus	MPa	220	ISO 178
Hardness, Shore D	-	50	ISO 868

MFR is measured from granulates.

Test specimen: injection moulded rod; ISO 527 TYPE 1A; Thickness: 10 mm, width: 4 mm

(* extruded tape; ISO 527-2 Type 5A, thickness 400 - 800 µm)

Item Description

Item ID

PRE-ELEC[®] CC2201
CC2201

Visit Premix Data Center for more detailed information of our products at

www.premixgroup.com/data-center/

Processing instructions

	Unit	Processing range		
Extrusion				
Cylinder temperature profile	°C	170	-	210
Die temperature profile	°C	180	-	230

Notes

Drying of the product is recommended for 2-3 hours at 60-80°C prior to use.

These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns. Overheated material can be cooled with e.g. water.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] is a registered trademark of Premix.