



PRE-ELEC[®] CC5101
CC5101

Item Description

Item ID

PE extrusion compound
Semiconductive
Good adhesion to metals

Typical end product
Polymer-to-metal adhesive

Applications
Cables
Laminated structures

PRE-ELEC[®] CC5101 is a conductive thermoplastic adhesive compound based on PE. The grade has good adhesion to aluminium and copper. Conductivity is achieved by using special conductive carbon black. In addition to a low electrical resistivity it has a balance of mechanical properties and is easy to extrude. It can be used as adhesive layer between PE and metal surface.

Special properties	Unit	Value	Method
--------------------	------	-------	--------

Volume resistivity(*)	Ω.cm	20	PRE021
-----------------------	------	----	--------

General properties	Unit	Value	Method
--------------------	------	-------	--------

Density	g/cm ³	1,03	ISO 1183
Melt flow rate at 190°C	g/10 min		ISO 1133
2.16 kg		0,7	
5.0 kg		3,2	
Vicat, Rate A	°C	81	ISO 306/A50
Vicat, Rate B	°C	45,0	ISO 306/B50

Mechanical properties	Unit	Value	Method
-----------------------	------	-------	--------

Stress at break	MPa	22	ISO 527
Strain at break	%	130	ISO 527
Hardness, Shore D	-	50	ISO 868

MFR is measured from granulates.

Test specimen: injection moulded rod; ISO 527 TYPE 1A; Thickness: 10 mm, width: 4 mm

(* extruded tape; ISO 527-2 Type 1B, thickness 400 - 800 µm



Item Description

Item ID

PRE-ELEC[®] CC5101
CC5101

Visit Premix Data Center for more detailed information of our products at www.premixgroup.com/data-center/

Processing instructions

	Unit	Processing range
Extrusion	Cylinder temperature profile	140 - 200
	Die temperature profile	160 - 200

Notes

Drying of the product is recommended for 0 hours at 0°C prior to use.

Metal surfaces in direct contact with the compound should be corrosion resistant or nickel/chrome plated. Flush the extrusion line before and after the run with LDPE or suitable cleaning compound. These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] is a registered trademark of Premix.