

PRE-ELEC[®] TPU 16619

Polyether-TPU extrusion compound
Electrically conductive

Applications: Hoses, conveyor belts
Profiles, Tape

PRE-ELEC[®] TPU 16619 is a conductive thermoplastic elastomer compound based on a polyether thermoplastic polyurethane (TPU). Conductivity is achieved by using special conductive carbon black. In addition to a low electrical resistivity, it has retained the excellent mechanical properties of the base elastomer. The grade is suitable for extrusion and injection moulding applications.

Special properties	Unit	Value	Method
Volume resistivity(*)	Ω.cm	30	PRE021
Surface resistance (*)	Ω	2E+03	IEC 61340-2-3

General properties	Unit	Value	Method
Specific gravity	g/cm ³	1.21	ISO 1183
Melt flow rate at 190°C 5.0 kg	g/10 min	5.0	ISO 1133

Mechanical properties	Unit	Value	Method
Tensile strength (*)	MPa	25	ISO 527
Tensile strain at break (*)	%	900	ISO 527
Tensile stress at 100% (*)	MPa	8	ISO 527
Tensile stress at 200% (*)	MPa	11	ISO 527
Tensile stress at 300% (*)	MPa	13	ISO 527
Tensile modulus (*)	MPa	50	ISO 527
Hardness, Shore A	-	88	ISO 868

MFR is measured from granulates

Test specimen: injection moulded rod; Thickness: 10 mm, width: 4 mm

*) extruded tape; Thickness 600-800 µm

PRE-ELEC[®] TPU 16619

This product is REACH and RoHS compliant

Visit Premix Data Center for more detailed information of our products at www.premixgroup.com/data-center-main

Processing instructions

	Unit	Processing range		
Extrusion				
Cylinder temperature profile	°C	165	-	190
Die temperature profile	°C	170	-	180
Tool/Roll temperature	°C	40	-	40
Injection moulding				
Material temperature	°C	180	-	210
Mould temperature	°C	20	-	40
Injection pressure	Bar	200	-	800
Injection speed		low		

Notes

Drying of the product is recommended for 3 hours at 80-90°C prior to use.

Processing conditions as with filled Polyether-TPU. The moisture content after drying should be less than 200 ppm in order to avoid loss of properties. The shelf life for this product is 1 year from the date of delivery with the same conditions as written below. These parameters are for guidance only. The process parameters should always be optimized for the used equipment. The instructions of the equipment manufacturer should be followed. Caution should be taken when handling molten material as it is extremely hot and may cause severe burns.

Storage

Product-specific details are mentioned in the notes above. The general minimum shelf life for Premix's product is 3 years with the following conditions: 1) original package is unopened, 2) the storage area and conditions provide protection from direct sunlight and significant changes in storage temperature, 3) the product is pre-dried accordingly before use.

The information in this datasheet represents typical values obtained by us, and shall not be regarded as a product specification. The right to make any changes to the content and appearance of this document is reserved by Premix Oy. We condition that the product will be inspected and qualified by the customer for their process to meet the specific requirements set by application, processing equipment and the end product. The user of this product is held responsible for the evaluation of this product's suitability concerning applied legislation and possible patent infringements. We do not intentionally add or incorporate hazardous substances in our production.

PRE-ELEC[®] is a registered trademark of Premix.